MEDICOM[®]

Technical Data Sheet

1

Safetouch® Latex Powdered Medical Examination Gloves

Item Code	1125 A-E		
Country of Origin	Thailand	SAFETOUCH	
Residual Powder Content	\leq 10 mg/ dm ²	Thailand $\leq 10 \text{ mg/ dm}^2$	
Maximum Protein Content	$10 \ \mu g/dm^2$	Smooth Lideox Medical Examination Games	
Length	_	\geq 220 mm for sizes XS & S \geq 230 mm for sizes M, L & XL	
Width	Extra-Small (X-S) Small (S) Medium (M) Large (L) Extra-Large (X-L)	≤ 80 70-90 85-105 100-120 ≥ 110	
Palm Thickness	0.08 - 2.0 mm	0.08 - 2.0 mm	
Finger Tip Thickness	$\geq 0.08 \text{ mm}$	$\geq 0.08 \text{ mm}$	
Force At Break Point		Before Aging: \geq 7.0 N After Aging: \geq 6.0 N	
Elongation %		Before Aging: $\geq 650 \%$ After Aging: $\geq 500 \%$	
Sterility	Non-Sterile	Non-Sterile	
Color	Natural rubber latex	Natural rubber latex (yellowish)	
Sizes	X-small, Small, Med	X-small, Small, Medium, Large, X- Large	
Glove Interior	Powdered	Powdered	
Glove Exterior	Smooth	Smooth	
Usage	For Single-use only	For Single-use only	
Packaging	100 gloves per dispenser box / 10 boxes per case / 1000 gloves per case		
Storage	excessive heat (40°C	Store under cool, dry place. Avoid excessive heat (40°C, 104°F). Shield open	
This glove meets ISO 11193-1	box from direct sun a lighting.	box from direct sun and fluorescent lighting.	
TDS #1125 Latex PP Rev 03	July 04, 2012	Marketing SR	